



TCI Sanmar Chemicals S.A.E

Polyvinyl Chloride PVC K-5701

K-5701 is a low molecular weight Polyvinyl Chloride homopolymer suspension resin produced by suspension process

Parameter	Test Procedure	Unit	Typical Value
K-Value	INEOS PM01	Number	57 ± 1
Partical size < 63 µm (230 mesh)	ASTM D 1921-06	%	10.0 max
Partical size > 250 µm (60 mesh)	ASTM D 1921-06	%	5.0 max
Bulk Density	ASTM D 1895-03	g/ml	0.50 ± 0.05
Dark Resin (in 100 gms)	INEOS PM06	Number	25 max
Heat Loss	ASTM D 3030-06	%	0.3 max

Application

Fittings for PVC Pipe
Rigid Injection Molded Products
Calendering Sheet & Film

Packaging

1 MT Jumbo woven sacks bag with inner liners

Head Office: Industrial Area C9, El Raswa, South Port Said, Egypt
Phone: +20663778000, Mobile: +201066682606, Fax: +20663778003-6
Email: tci@tci.sanmargroup.com www.sanmargroup.com
A constituent of Sanmar Chemicals Corpn