

• DESCRIPTION

PP H040 GP is a bimodal propylene homopolymer with standard stabilizers providing heat stability, resistance to corrosion, resistance to thermo-oxidative degradation.

• APPLICATION

PP H040 GP is designated for extrusion and molding of industrial application products, production of raffia and mixtures.

PROPERTIES	TEST CONDITIONS	TEST STANDARD	TYPICAL VALUE *
Physical			
Melt Flow Index, g/10 min	(230 °C/2.16 kg)	ISO 1133 or GOST 11645	3.5-4.9
Mechanical			
Tensile Yield Strength, MPa	(50 mm/min)	ISO 527 or GOST 11262	34
Elongation at Yield, %	(50mm/min)	ISO 527 or GOST 11262	10
Flexural Modulus, MPa	(2 mm/min)	GOST 9550	1400
Isod Impact Strength, Notched, kJ/m ²	(+23 °C)	ISO 180 or GOST 19109	5.0
Thermophysical			
Vicat Softening Point, °C	(10 N)	ISO 306 or GOST 15088	155
Heat Deflection Temperature, °C	(0.45 MPa)	ISO 75 or GOST 12021	110

*Typical value; not for the specification.

Drawn: March 2013

The information provided in the present document is accurate and reliable and is correct at the time of going to print. The TITAN Company does not guarantee or claim the information provided in the present document to be accurate or complete, and disclaims any responsibility for the consequences resulting from using the information and is not liable for any misprints. Our products are designated for sale to industrial and commercial customers. Conduction of the tests for determination of applicability of the products for particular usage is the customer's responsibility. The customer is also responsible for our products processing as well as appropriate, safe and legal use.